

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : A61K 6/10, C08L 83/04	A1	(11) International Publication Number: WO 00/48553 (43) International Publication Date: 24 August 2000 (24.08.00)
(21) International Application Number: PCT/US99/29113 (22) International Filing Date: 8 December 1999 (08.12.99) (30) Priority Data: 09/250,927 18 February 1999 (18.02.99) US (71) Applicant: KERR CORPORATION [US/US]; 1717 West Collins Avenue, Orange, CA 92867 (US). (72) Inventors: WALLER, Duncan, E.; 7993 Mallard Way, Ypsilanti, MI 48197 (US). XIE, Xiaoyi; 400 East Live Oak Street #19, San Gabriel, CA 91776 (US). (74) Agents: DAVIDSON, Kristi, L. et al.; Wood, Herron & Evans, L.L.P., 2700 Carew Tower, Cincinnati, OH 45202 (US).		(81) Designated States: BR, CN, JP, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: HYDROPHILICALLY MODIFIED CURABLE SILICONE IMPRESSION MATERIAL (57) Abstract <p>The present invention provides hydrophilically modified curable silicone dental impression materials comprising an addition curable silicone prepolymer composition and a polymerizable hydrophilic modifier. The addition curable silicone prepolymer in the composition of the present invention comprises blended vinyl terminated organopolysiloxane fluids, an organohydrogen polysiloxane crosslinker, a platinum catalyst, a retarder, filler and optional additives. The cured compositions have a stable hydrophilic nature, excellent mechanical properties, and maximum long-term dimensional stability.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
RJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

-1-

HYDROPHILICALLY MODIFIED CURABLE SILICONE IMPRESSION MATERIAL

Field of the Invention

This invention relates to a curable silicone impression material, in particular, a dental impression material having a stable hydrophilic nature, excellent mechanical properties, and maximum long-term dimensional stability.

5 Background of the Invention

Curable silicone compositions, especially the addition-curable silicone compositions, are widely used as dental impression materials. Generally, the addition-curable silicone compositions have the advantages of fast curing speed and low shrinkage. Furthermore, the cured silicone compositions have excellent physical

10 properties, such as high mechanical strength and good dimensional stability. A considerable disadvantage of silicone compositions of this type, however, is their high hydrophobicity, which makes it difficult for them to take precise impressions when used on wet surfaces, such as the tissue, tooth or dental prosthesis in the oral environment in which blood, saliva, or other fluids usually exist.

The preparation of dental silicone impression materials by incorporating hydrocarbon, fluorocarbon or silicone-based surfactants, including ionic- and nonionic-type surfactants is known for imparting hydrophilic properties to these inherently hydrophobic substances and for improving the surface wettability. However, the addition of one or more surfactants to the compositions of the silicone polymers to impart hydrophilicity has drawbacks in that the surfactant molecules have a tendency to demix from the impression materials or migrate to the surface thereof, or the molecules are extracted from the impression material when it is contacted with aqueous media. Thus, the hydrophilicity of the impression materials cannot be retained when subjected to the procedures of rinsing with water, disinfection and sterilization required in dental clinic practice. Furthermore, when the surfactant is added in a large amount to obtain satisfactory water wettability of the cured silicone composition, the curing reaction of the composition is hindered, and the cured silicone composition has poor physical properties such as low tensile strength, elongation and tear strength. Particularly, the loss of surfactant due to contact with aqueous media results in undesirable dimensional change of the cured silicon composition.


Attempts have been made to render silicone dental impression materials more hydrophilic by adding hydrophilic additives into the curable silicone compositions. Hittmair et al. in U.S. Patent No. 4,035,453 discloses the methods of making dental impression materials using curable silicone compositions. Bryan et al. in U.S. Patent No. 4,657,959 and Aasen et al. in U.S. Patent Nos. 4,691,039 and 4,752,633 disclose adding an ethoxylated nonionic surfactant containing siloxane or perfluoroalkyl solubilizing groups to achieve a three-minute water contact angle below about 65°. Fujiki et al. in U.S. Patent No. 5,064,891 discloses a curable silicone composition comprising a nonionic surface active agent having a hydrophobic silicone portion and at

least one hydrophilic polyol portion in its molecule. Kamohara et al. in U.S. Patent No. 5,637,628 discloses a dental impression-taking silicone composition comprising a polyvinyl ether having a degree of polymerization of 1,000 to 50,000. Hare in U.S. Patent Nos. 5,661,222 and 5,863,965 and Fiedler in U.S. Patent No. 5,830,951 disclose
5 two-component polymerizable polyvinylsiloxane compositions comprising mono- and quadri-functional resins (QM) and nonylphenoxypoly (ethyleneoxy) ethanol surfactant. Zech et al. in U.S. Patent No. 5,750,589 discloses a dental impression material containing polyether carbosilane as a hydrophilation agent. Jada in U.S. Patent No. 5,852,068 discloses a dental impression composition comprising a dimethicone-based
10 polysiloxane polyester polymer having terminal fluorinated alkoxy substituents. Paradiso in WO 93/17654 discloses a dental impression material comprising mono and quadri-functional QM resins. Gribi in EP 0 231 420 B1 describes the use of siloxane components having polyether moieties in the molecule.

The prior art hydrophilic additives in the silicone impression compositions suffer
15 from certain drawbacks including unstable hydrophilicity when in contact with aqueous media and reduction in the physical properties such as tensile strength, elongation and tear strength. Accordingly, it would be desirable to provide an improved curable silicone impression material having a stable hydrophilic nature, excellent mechanical properties, and maximum long-term dimensional stability.

20 **Summary of the Invention**

The present invention provides a curable silicone composition comprising a mixture of: (a) an addition-curable silicone prepolymer; and (b) at least one polymerizable hydrophilic modifier that is a functional hydrophilic polysiloxane having the general formula:



wherein functional group R is a vinyl group or a hydrogen atom; R¹ is a C₁ to C₃ univalent hydrocarbon radical; Q is a hydrogen atom or a monovalent hydrocarbyl radical; n is an integer greater than or equal to three; x is an integer greater than or equal to zero; y is an integer greater than or equal to one; p is an integer greater than or equal to one; and q is an integer greater than or equal to zero.

The present invention further provides a method for making a dental impression comprising the step of making a negative mold of oral tissue using a hydrophilically modified curable silicone composition of the present invention.

These and other objects and advantages of the present invention shall become
10 more apparent from the following description.

Detailed Description

The hydrophilically modified silicone impression material of the present invention is characterized by good wettability, excellent physical strength, and maximum long-term dimensional stability.

15 In the composition of the present invention, the hydrophilically modified silicone impression material is a two component room temperature vulcanization (RTV) addition cure vinyl polysiloxane material. The composition of the present invention in general comprises a mixture of an addition-curable silicone prepolymer and a polymerizable hydrophilic modifier. The addition-curable silicone prepolymer typically

comprises the following components: (a) at least one vinyl terminated organopolysiloxane fluid having at least about two vinyl groups per molecule; (b) at least one organohydrogen polysiloxane crosslinker having at least about three silicon hydride groups per molecule; (c) a platinum catalyst; (d) a retarder; (e) filler; and (f) optional additives.

The composition of the present invention preferably comprises a catalyst paste and a base paste in intimate admixture with one another in a paste/paste system in which curing is initiated by means of a platinum-catalyzed hydrosilation (addition) reaction between the vinyl-functional polysiloxane and the hydride-functional polysiloxane crosslinker. Generally, the catalyst paste comprises vinyl terminated organopolysiloxane fluid, a platinum catalyst for accelerating the addition reaction, a retarder for delaying the curing to ensure a sufficient working time, a hydrogen scavenger for entrapping hydrogen released during polymerization, fillers for reinforcing and/or non-reinforcing (extending) purposes, and pigments. The base paste generally comprises vinyl terminated organopolysiloxane fluid, an organohydrogen polysiloxane crosslinker, a hydrophilic modifier, fillers, and pigments.

The vinyl terminated organopolysiloxanes having at least about two vinyl groups per molecule are well-known to those of ordinary skill in the art. Preferred for use herein are linear vinyl terminated organopolysiloxanes. Most commonly-used vinyl terminated organopolysiloxanes have a methyl substituent, for example, vinyl terminated polydimethylsiloxane. Other substituents such as alkyl, aryl, halogen, and the like may also be included for any particular application of the composition in accordance with the principles of this invention. The commercial vinyl terminated polydimethylsiloxanes have a wide variety of molecular weights with viscosities ranging from about 100 to about 1,000,000 centistoke. However, when the viscosity is

too high, the vinyl terminated polydimethylsiloxane fluid is too viscous to formulate into free flowing dental impression materials, which is necessary for easy mixing and handling. In practice, it has been found that suitable vinylpolysiloxane fluids with viscosity lower than about 100,000 centistoke may be successfully blended with suitable
5 fillers and other desirable additives to produce superior dental impression materials. Preferably, a blend of vinylpolysiloxane fluids having different viscosities ranging from about 100 to about 60,000 centistoke is used to provide compositions having a desired thixotropicity and viscosity, and more importantly to provide cured compositions having desired physical properties. The lower viscosities within this range contribute to higher
10 crosslink densities and provide elastomer stiffness and high deformation recovery, while the higher viscosities within the range provide for higher elasticity and elongation.

The organohydrogen polysiloxane crosslinker useful in the composition of the present invention is organopolysiloxane having at least three hydrogen atoms per molecule directly bonded to silicon atoms. The most commonly-used organohydrogen
15 polysiloxane crosslinkers have a methyl substituent, for example, polymethylhydrosiloxane, methylhydro dimethyl polysiloxane copolymers, and combinations thereof. Other substituents such as alkyl, aryl, halogen, and the like may also be employed for any particular application of the composition in accordance with the principles of this invention. Preferably, the polymethylhydrosiloxane has a viscosity range of about 2 to
20 about 300 centistoke, and most preferably about 3 to about 45 centistoke.

One type of catalyst useful for catalyzing the addition reaction between the vinyl-functional polysiloxane molecules and the hydride-functional polysiloxane crosslinkers is a platinum-based catalyst. In this regard, it is preferred to employ a platinum compound such as chloroplatinic acid. The concentration of platinum and
25 platinum compounds ranges from about 5 ppm to about 500 ppm, preferably about

5 ppm to about 200 ppm, based on the weight of the catalyst component. Preferably, the platinum and platinum compounds are used in admixture or complex with one or more vinyl-containing molecules, especially vinyl polysiloxanes in a concentration range of about 0.1 wt.% to about 5 wt.% platinum, preferably about 0.5 wt.% to about 2 wt.%.
5 Other catalysts useful in the practice of the present invention are those based on other noble metals including palladium, rhodium, and the like, and their respective complexes and salts. In view of the toxicological acceptability of platinum, however, it is preferred for dental use.

A retarder is provided in the composition of the present invention for delaying
10 the onset of the addition reaction between the vinyl-functional polysiloxane and the hydride-functional polysiloxane crosslinker such that sufficient working time for mixing and applying the composition is achieved. The retarder functions, as it is consumed, as a "chain stopper" to provide sufficient induction time and to allow seating of the impression tray over the dentition prior to the occurrence of any significant increase in
15 viscosity of the mixed paste. The preferred work time is greater than 1 minute and less than 5 minutes, and preferably about 1 to 2 minutes. Suitable retarders are any low molecular weight, vinyl functional linear or cyclic polysiloxane fluid that would be initially consumed in the polymerization reaction to delay curing for the desired time period. The preferred retarder fluid is 1,3,5,7-tetravinyltetramethylcyclotetrasiloxane,
20 which is present in the composition at a sufficient concentration level to perform its retarding functions. The preferred retarder is present at a concentration of at least about 0.01 wt.% of the composition, and preferably at a concentration within a range of about 0.01 to about 0.10 wt.%. Another suitable retarder fluid is 1,3-divinyltetramethyldisiloxane.

The fillers useful in the composition of the present invention include reinforcing and/or non-reinforcing (extending) fillers. Suitable reinforcing fillers include fumed silica, carbon black, and the like. The addition of reinforcing filler improves the mechanical strength, such as the tensile and tear strengths, of the cured silicone composition. Suitable non-reinforcing fillers include precipitated silicas, diatomaceous earth, aluminas, magnesias, titanium dioxide, zirconium silicate, calcium carbonate, metallic oxides, and the like. Surface-treated fillers may also be used. Typical surface treatments includes silanization and the like. In accordance with the principles of the present invention, it is preferable to employ mixtures of fillers with different particle sizes. Preferably, a bimodal filler system blended with sub-micron ($< 1\mu\text{m}$) and micron sized particles ($2-10\mu\text{m}$) of close particle size distribution is used as a varying filler loading to provide dental impression materials with low, medium or high consistency suitable for use in all known dental impression techniques. The fillers are present, preferably, in amounts of from about 15 wt.% to about 50 wt.% of the composition. To adjust the consistency of the two-component composition to achieve either a low, medium or high consistency composition, the sub-micron sized filler and/or the micron sized filler may be adjusted in one or both of the catalyst and base pastes. The higher the consistency desired, the more beneficial it is to increase the sub-micron filler to a greater extent than the increase in the micron sized filler, whereby the sub-micron filler particles are worked into the interstitial spaces between micronized particles during mixing.

An optional hydrogen scavenger in the composition of the present invention is useful in controlling or preventing the presence of hydrogen gas that is evolved from the reaction from existing in the cured composition. The preferred hydrogen scavenger is a finely-divided platinum metal as described in U.S. Patent No. 4,806,575, which is


incorporated herein by reference in its entirety. Generally, the platinum metal is used at a concentration level of about 0.2ppm to about 20,000ppm, based on the weight of the catalyst component. The finely divided platinum metal may be added alone or may be blended with fillers described above, for example, calcium silicate, in a concentration
5 range of about 0.1 wt.% to about 5 wt.%, and preferably about 0.5 wt.% to about 2 wt.%. Another suitable hydrogen scavenger is palladium metal as described in U.S. Patent No. 5,684,060, which is incorporated herein by reference in its entirety.

A key improvement of the present invention is the use of a polymerizable hydrophilic modifier that imparts wettability to the composition of the present
10 invention. The hydrophilic modifier contains hydrophobic groups and hydrophilic groups in the molecule structure. The hydrophobic groups are one or more siloxane groups that render the modifier composition soluble or dispersible in the silicone prepolymer. The hydrophilic groups are water-loving groups that render the composition of the present invention hydrophilic. The water-loving groups are
15 ethyleneoxy ($-C_2H_4O-$) groups or propyleneoxy ($-C_3H_6O-$) groups. In the preferred composition of the present invention, the hydrophilic modifier contains polymerizable functional groups having one or more vinyl groups or one or more hydrogen atoms which directly bond to the silicon atoms of the polysiloxane molecules. One advantage of the polymerizable hydrophilic modifier is its ability to be incorporated into the cured
20 polysiloxane matrix formed by the addition curing reaction between the vinyl terminated organopolysiloxane and the organohydrogen polysiloxane crosslinker. Therefore, curing the composition of the invention immobilizes the hydrophilic component and forms a silicone polymer material including a hydrophilic constituent, preferably in an amount effective to provide enhanced or increased hydrophilicity to the
25 cured material, for example, relative to a substantially identical material without the

hydrophilic constituent. The hydrophilic constituent in the cured material does not demix from the impression composition nor migrate to the surface thereof, and it is not extracted from the impression material when it is contacted with aqueous media. The hydrophilicity of the cured material remains substantially unchanged after relatively

5 long contact with an aqueous system, for example, rinsing with water, disinfection and sterilization. More importantly, the cured material retains excellent physical properties such as tensile strength, elongation, tear strength and dimensional stability.

The polymerizable hydrophilic modifier in the composition of the present invention is a functional hydrophilic polysiloxane having the general formula:



10 wherein functional group R is a vinyl group or a hydrogen atom, preferably a vinyl group; R¹ is a C₁ to C₈ univalent hydrocarbon radical, and is preferably a methyl group; Q is a hydrogen atom or a monovalent hydrocarbyl radical, preferably a methyl group; n is an integer greater than or equal to 3, preferably 3; x is an integer greater than or equal to 0, preferably from 0 to about 300; y is an integer greater than or equal to 1, preferably

15 from about 1 to about 50; p is an integer greater than or equal to 1, preferably from about 2 to about 15; and q is an integer greater than or equal to 0, preferably from 0 to about 15.

Generally, the hydrophilic modifier can be produced by methods known in the art, for example, as disclosed in *Silicones Chemistry and Technology*, pp 111-122, CRC Press (1991), the disclosure of which is incorporated herein by reference in its entirety.

An example of a preferred hydrophilic modifier for use in the composition of the

5 present invention is commercially available from Wacker Silicones Corporation, Adrian, MI, under the product code SLM26616, wherein R is vinyl, R¹ is methyl, Q is methyl, n is 3, x is about 150, y is about 20-25, p is about 3-5, and q is zero.

The amount of hydrophilic modifier introduced into the curable silicone composition should be sufficient to provide the desired benefit, for example, enhanced
10 hydrophilicity, to the vinyl polysiloxane impression materials. The amount of hydrophilic modifier included in the final silicone polymer material varies widely depending on the specific hydrophilic constituent involved and the degree of hydrophilicity desired. Thus, the preferred amount of hydrophilic modifier of the present invention is in the range from about 0.1% to about 30% by weight, and more preferably
15 from about 1% to about 15% by weight, and most preferably from about 3% to about 10% by weight of the composition. The curable silicone composition contains a sufficient amount of hydrophilic modifier so that the silicone composition, when cured, has a three minute water contact angle below about 65°, and preferably has a one minute water contact angle below about 65°. The term "water contact angle" refers to
20 the contact angle formed by a drop of distilled water and measured at a specific time after it is applied to a cured composition of the invention, as measured at room temperature using a contact angle goniometer, for example, the model 100 version made by Rame-Hart, Inc, Mountain Lakes, NJ.

The hydrophilic modifier may be used alone, or in combination with one or
25 more surfactants in the addition-curable silicone prepolymer composition of the present

invention. The surfactants used can be cationic, anionic, amphoteric or nonionic. A preferred surfactant is a nonionic type comprising nonylphenoxypoly(ethyleneoxy) ethanol, available from Rhone-Poulenc, Cranbury, NJ, under the trade names IGEPAL® CO-520, CO-530 and the like. The use of such surfactants further enhances the hydro-
5 philicity of the cured silicone material because the nonylphenoxypoly(ethyleneoxy) ethanol is partially miscible with the hydrophilic modifier and has a synergistic effect with the modifier to improve the wettability of the cured composition.

Other additives which may be used in the present invention include plasticizers, pigments, dyes, flavors, perfumes, fluidity regulators, and the like provided that they do
10 not substantially affect cure.

Typically, the composition according to the present invention is packaged, stored, and used in the conventional manner for addition-curable silicone prepolymer systems. Thus, the catalyst and base components are generally stored separately. The hydrophilic modifier of the present invention may be present in either component, or
15 both. However, where the ingredients in the curable polysiloxane composition may react with constituents of either component, then it should be added only to the non-reactive component. The catalyst and base pastes are mixed together thoroughly in a ratio of from about 1:5 to about 5:1, and preferably about 1:1, and applied to the oral dentition or other region for a period of time sufficient for polymerization or hardening
20 of the composition. Once the composition has been substantially hardened, it is removed from the mouth or other surface and used for the elaboration of casts and the like from which representations of the casting surface are subsequently prepared.

The following examples further illustrate the embodiments of the present invention. Neither these examples nor any of the foregoing disclosure should be

construed as limiting in any way the scope of the present invention. Unless otherwise indicated, all parts and percentages are by weight.

EXAMPLE 1

This is a low consistency two-component composition according to the principles of the present invention, which is formulated in catalyst paste and base paste components. Mixing of each of the catalyst and base pastes is accomplished in a planetary mixer, and the resulting pastes may be milled in a three roll mill to achieve final homogeneity. The composition of each component is indicated in the table below (all quantities expressed as weight percent).

	Catalyst Paste	Base Paste
10 Blend of vinyl terminated polydimethylsiloxanes (200-60,000 cSt.)	79.37	66.7
Polymethylhydrosiloxane crosslinker (30 cSt.)	—	8
Polymerizable hydrophilic modifier (SLM 26616)	—	5
Surfactant (IGEPAL [®] CO-520)	—	1.5
15 Platinum catalyst complex with vinylsiloxane (0.5-2.0 wt.%)	1.5	—
1,3,5,7-tetravinyltetramethylcyclotetrasiloxane	0.03	—
Finely divided platinum metal on calcium silicate (0.5-2.0 wt.%)	0.5	—
Pigments	0.2	0.4
20 Sub-micron silica (<1 μ m average particle size)	10	10
Calcium silicate Wollastonite (2-10 μ m average particle size)	8.4	8.4
Total	100	100

EXAMPLE 2

This is a medium consistency two-component composition according to the principles of the present invention having moderate thixotropy, which is formulated in catalyst paste and base paste components. Mixing of each of the catalyst and base

pastes is accomplished in a planetary mixer, and the resulting pastes may be milled in a three roll mill to achieve final homogeneity. The composition of each component is indicated in the table below.

	Catalyst Paste	Base Paste
5 Blend of vinyl terminated polydimethylsiloxanes (200-60,000 cSt.)	70.27	60.5
Polymethylhydrosiloxane crosslinker (30 cSt.)	—	8
Polymerizable hydrophilic modifier (SLM 26616)	—	5
Surfactant (IGEPAL® CO-520)	—	1.5
Platinum catalyst complex with vinylsiloxane (0.5-2.0 wt.%)	1.5	—
10 1,3,5,7-tetravinyltetramethylcyclotetrasiloxane	0.03	—
Finely divided platinum metal on calcium silicate (0.5-2.0 wt.%)	0.5	—
Pigments	0.25	0.5
Sub-micron silica (<1 μ m average particle size)	16	16
15 Calcium silicate Wollastonite (2-10 μ m average particle size)	11.45	8.5
Total	100	100

EXAMPLE 3

This is a high consistency two-component composition according to the principles of the present invention having high thixotropy, which is formulated in catalyst paste and base paste components. Mixing of each of the catalyst and base pastes is accomplished in a planetary mixer, and the resulting pastes may be milled in a three roll mill to achieve final homogeneity. The composition of each component is indicated in the table below.

	Catalyst Paste	Base Paste

5	Blend of vinyl terminated polydimethylsiloxanes (200-60,000 cSt.)	64.27	58
	Polymethylhydrosiloxane crosslinker (30 cSt.)	—	8
	Polymerizable hydrophilic modifier (SLM 26616)	—	5
	Surfactant (IGEPAL® CO-520)	—	1.5
	Platinum catalyst complex with vinylsiloxane (0.5-2.0 wt.%)	1.5	—
10	1,3,5,7-tetravinyltetramethylcyclotetrasiloxane	0.03	—
	Finely divided platinum metal on calcium silicate (0.5-2.0 wt.%)	0.5	—
	Pigments	0.38	0.5
	Sub-micron silica (<1 μ m average particle size)	20	19
	Calcium silicate Wollastonite (2-10 μ m average particle size)	13.32	8
	Total	100	100

EXAMPLE 4

15 In comparison with Example 1, this example illustrates the effect of the addition of a non-polymerizable hydrophilic additive, such as an ethoxylated surfactant SILWET® L-77, available from Witco Corp., Greenwich, CT, and generally described in U.S. Patent No. 4,657,959 into the silicone composition. As will be shown in the table below, use of this additive results in poor physical properties in the cured

20 composition even though a high wetting capability and low water contact angle are achieved. The catalyst and base pastes are prepared as described in Example 1. The composition of each component is indicated in the table below.

25		Catalyst Paste	Base Paste
	Blend of vinyl terminated polydimethylsiloxanes (200-60,000 cSt.)	79.47	68.75
	Polymethylhydrosiloxane crosslinker (30 cSt.)	—	8
	Hydrophilic additive (SILWET® L-77)	—	5

5	Surfactant (IGEPAL [®] CO-520)	—	0
	Platinum catalyst complex with vinylsiloxane (0.5-2.0 wt.%)	1.5	—
	1,3,5,7-tetravinyltetramethylcyclotetrasiloxane	0.03	—
	Finely divided platinum metal on calcium silicate (0.5-2.0 wt.%)	0.5	—
	Pigments	0.5	0.25
	Sub-micron silica (<1 μ m average particle size)	10	10
	Calcium silicate Wollastonite (2-10 μ m average particle size)	8	8
	Total	100	100

10 EXAMPLE 5

In comparison with Example 1, this example again illustrates the effect of the addition of a non-polymerizable hydrophilic additive into the silicone composition. As will be shown in the table below, use of this additive results in poor physical properties in the cured composition even though a high wetting capability and low water contact angle are achieved. The catalyst and base pastes are prepared as described in Example 1. The composition of each component is indicated in the table below.

		Catalyst Paste	Base Paste
20	Blend of vinyl terminated polydimethylsiloxanes (200-60,000 cSt.)	79.47	66.25
	Polymethylhydrosiloxane crosslinker (30 cSt.)	—	8
	Hydrophilic additive (SILWET [®] L-77)	—	5
	Surfactant (IGEPAL [®] CO-520)	—	0
	Platinum catalyst complex with vinylsiloxane (0.5-2.0 wt.%)	1.5	—
	1,3,5,7-tetravinyltetramethylcyclotetrasiloxane	0.03	—
	Finely divided platinum metal on calcium silicate (0.5-2.0 wt.%)	0.5	—
25	Pigments	0.5	0.25
	Sub-micron silica (<1 μ m average particle size)	10	10

Calcium silicate Wollastonite (2-10 μ m average particle size)	8	8
Total	100	100

EXAMPLES 1-5

A representative sample of each paste composition for each of the above-described examples is mixed accordingly in equal volumes. The physical properties of the cured compositions are determined, using ISO Specification No. 4823 for evaluation of work time, set time, mixed consistency, dimensional change, strain in compression and deformation recovery; and ASTM Standards for the evaluation of shore A hardness (ASTM D2240), tensile strength (ASTM D412), elongation (ASTM D412) and tear strength (ASTM 624). The water contact angle is measured at 60 seconds after a drop of distilled water is applied to a cured composition of the invention, at room temperature using a contact angle goniometer (model 100 made by Rame-Hart, Inc.). The results are reported in the following table.

	Example				
	1	2	3	4	5
Work time (min.)	1.5	1.5	1.5	1.5	1.7
Set time (min.)	4	4	4	4	4
Mixed consistency (mm)	43	31.3	27	—	—
Dimensional change at 24 hr. (%)	0.16	0.33	0.28	0.33	0.3
Strain in compression (%)	4.7	4.5	4.35	5.8	—
Deformation recovery (%)	99.8	99.7	99.7	99.6	98.57
Hardness (Shore A)	40	50	67	36	36
Tensile strength (Mpa)	2.52	3.5	3.81	1.84	1.68
Elongation (%)	400	406	420	392	428
Tear Strength (Die C) (N/mm)	5.27	7.7	9.37	5.22	4.69
Contact angle (at 1 min.) (deg.)	26	29	31	8	7

While the present invention has been illustrated by the description of an embodiment thereof, and while the embodiment has been described in considerable detail, it is not intended to restrict or in any way limit the scope of the appended claims to such detail. Additional advantages and modifications will readily appear to those skilled in the art. The invention in its broader aspects is therefore not limited to the specific details, representative method and illustrative examples shown and described. Accordingly, departures may be made from such details without departing from the scope or spirit of applicant's general inventive concept.


WHAT IS CLAIMED IS:

1. A curable silicone composition for use as a dental impression material, comprising:

an addition-curable silicone prepolymer; and

at least one polymerizable hydrophilic modifier that is a functional

5 hydrophilic polysiloxane having a general formula of:



wherein functional group R is a vinyl group or a hydrogen atom; R¹ is a C₁ to C₈ univalent hydrocarbon radical; Q is a hydrogen atom or a monovalent hydrocarbon radical; n is an integer greater than or equal to three; x is an integer greater than or equal to zero; y is an integer greater than or equal to one; p is an integer greater than or equal to one; and q is an integer greater than or equal to zero.

2. The composition of claim 1, wherein the addition-curable silicone prepolymer comprises: (a) at least one vinyl terminated organopolysiloxane fluid; (b) at least one organohydrogen polysiloxane crosslinker; (c) a noble metal-based catalyst; (d) a retarder; and (e) filler.

3. The composition of claim 2, wherein the composition is a paste/paste system including a catalyst paste and a base paste, the catalyst paste comprising (a) at least one vinyl terminated organopolysiloxane fluid, (b) the noble metal-based catalyst, (c) the retarder, (d) a hydrogen scavenger and (e) filler; and the base paste comprising
- 5 (a) at least one vinyl terminated organopolysiloxane fluid, (b) at least one organohydrogen polysiloxane crosslinker, (c) the hydrophilic modifier, and (d) filler.
4. The composition of claim 2, wherein the vinyl terminated organopolysiloxane fluid comprises at least two vinyl groups per molecule bonded directly to silicon atoms.
5. The composition of claim 4, wherein the vinyl terminated organopolysiloxane fluid comprises linear vinyl terminated organopolysiloxane having a substituent selected from the group consisting of: methyl, alkyl, aryl, halogen, and combinations thereof.
6. The composition of claim 5, wherein the vinyl terminated organopolysiloxane fluid comprises at least one vinyl terminated polydimethylsiloxane fluid.
7. The composition of claim 6, wherein the at least one vinyl terminated polydimethylsiloxane fluid includes a blend of fluids having different molecular weights, each fluid having a viscosity in the range of about 100 to about 100,000 centistoke.

8. The composition of claim 2, wherein the organohydrogen polysiloxane crosslinker comprises organopolysiloxane having at least three hydrogen atoms per molecule bonded directly to silicon atoms, and having a substituent selected from the group consisting of: methyl, alkyl, aryl, halogen, and combinations thereof.
9. The composition of claim 8, wherein the crosslinker is an organohydrogen polysiloxane selected from the group consisting of polymethylhydrosiloxane, methylhydro dimethyl polysiloxane copolymer, and combinations thereof.
10. The composition of claim 9, wherein the polymethylhydrosiloxane has a viscosity range of about 2 to about 300 centistoke.
11. The composition of claim 2, wherein the noble metal-based catalyst is a platinum-based catalyst.
12. The composition of claim 2, wherein the retarder is a polysiloxane fluid selected from the group consisting of: low molecular weight, vinyl functional linear polysiloxane and low molecular weight, vinyl functional cyclic polysiloxane.
13. The composition of claim 2, wherein the filler is present in an amount of about 15 to about 50 wt. % of the composition.
14. The composition of claim 13, wherein the filler is a blend of sub-micron sized filler particles and micron sized filler particles.

15. The composition of claim 2, further comprising a hydrogen scavenger.
16. The composition of claim 1, wherein R is a vinyl group, and R¹ and Q are methyl groups.
17. The composition of claim 1, wherein n equals 3, x equals 0 to about 300, y equals about 1 to about 50, p equals about 2 to about 15, and q equals 0 to about 15.
18. The composition of claim 1, wherein R is a vinyl group. R¹ and Q are methyl groups. n equals 3, x equals about 150, y equals about 20 to 25, p equals about 3 to about 5, and q equals 0.
19. The composition of claim 1, wherein the hydrophilic modifier is present in an amount of about 0.1 to about 30 wt. % of the composition.
20. The composition of claim 1, wherein the hydrophilic modifier is present in an amount sufficient to achieve a three minute water contact angle below about 65° in the composition after curing.
21. The composition of claim 1, further comprising a surfactant, wherein the surfactant is at least partially miscible with the hydrophilic modifier.
22. The composition of claim 21, wherein the surfactant is nonylphenoxy-poly (ethyleneoxy) ethanol.

23. A method of making a dental impression comprising the step of making a negative mold of oral tissue using a curable silicone composition of claim 1.
24. A method of making a dental impression comprising the step of making a negative mold of oral tissue using a curable silicone composition of claim 2.
25. A method of making a dental impression comprising the step of making a negative mold of oral tissue using a curable silicone composition of claim 3.
26. A method of making a dental impression comprising the step of making a negative mold of oral tissue using a curable silicone composition of claim 21.

- 27. A dental impression comprising a cured silicone composition of claim 1.
- 28. A dental impression comprising a cured silicone composition of claim 2.
- 29. A dental impression comprising a cured silicone composition of claim 3.
- 30. A dental impression comprising a cured silicone composition of claim 21.

INTERNATIONAL SEARCH REPORT

Intern. Nat. Application No.

PCT/US 99/29113

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61K6/10 C08L83/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 885 932 A (OSI SPECIALTIES INC) 23 December 1998 (1998-12-23)	1-13, 16-18, 27-29
Y	page 4, line 6 page 4, line 35 - page 5, line 57 page 7, line 5 - line 11 claims	1, 15, 21-26
X	DE 41 29 613 A (WACKER CHEMIE GMBH) 11 March 1993 (1993-03-11) page 4, line 44 - line 54 page 6, line 21 - line 25 & US 5 852 068 A cited in the application	1-3

-/-

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 April 2000

Date of mailing of the international search report

20/04/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Cousins-Van Steen, G

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Nat. Application No

PCT/US 99/29113

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0885932	A	23-12-1998	BR 9802020 A CA 2240924 A JP 11071460 A	29-06-1999 18-12-1998 16-03-1999
DE 4129613	A	11-03-1993	AT 131029 T BR 9206465 A CA 2115663 A,C CN 1070206 A,B DE 59204623 D WO 9304659 A EP 0602128 A ES 2080515 T JP 6506017 T JP 2558060 B KR 147421 B MX 9205076 A US 5580921 A US 5852068 A	15-12-1995 31-10-1995 18-03-1993 24-03-1993 18-01-1996 18-03-1993 22-06-1994 01-02-1996 07-07-1994 27-11-1996 17-08-1998 01-03-1993 03-12-1996 22-12-1998
DE 4433139	A	21-03-1996	AU 698620 B AU 3607195 A WO 9608230 A EP 0729341 A JP 9505322 T US 5750589 A	05-11-1998 29-03-1996 21-03-1996 04-09-1996 27-05-1997 12-05-1998
DE 19525468	A	16-01-1997	NONE	
WO 9853791	A	03-12-1998	EP 0986362 A	22-03-2000



Creation date: 10-15-2003

Indexing Officer: KCHALUENSOUK - KHAM-OUNE CHALUENSOUK

Team: OIPEScanning

Dossier: 10622257

Legal Date: 09-29-2003

No.	Doccode	Number of pages
1	IDS	7
2	FOR	7
3	FOR	19
4	NPL	1
5	NPL	1

Total number of pages: 35

Remarks:

Order of re-scan issued on